



烟台龙义兴高分子材料有限公司
Longyixing Chemicals Co., Ltd

✉ www.ilongchem.com

🌐 sales@ytlyx.com

LLDPE 222WT

LINEAR LOW DENSITY POLYETHYLENE

DESCRIPTION

222WT is an ethylene-butene copolymer designed for blown film application. 222WT has superior film mechanical property like stiffness, puncture resistance and tensile strength, it also has excellent sealing property, 222WT contains high slip and high antiblock.

TYPICAL APPLICATIONS

Cloth bag, carrier bag, thin layer coating, refuse bag, meat packaging and other food packaging or lamination film ,general purpose consumer packaging etc.

TYPICAL PROPERTY VALUES

Revision 20201104

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
@ 190°C & 2.16 kg	1.9	g/10 min	ASTM D1238
Density at 23°C	922	kg/m³	ASTM D1505
FORMULATION			
Slip agent	☑	-	-
Anti block agent	☑	-	-
MECHANICAL PROPERTIES			
Tensile test			
stress at yield, MD	10	MPa	ASTM D882
stress at yield, TD	10	MPa	ASTM D882
stress at break, MD	31	MPa	ASTM D882
stress at break, TD	23	MPa	ASTM D882
elongation at break, MD	450	%	ASTM D882
elongation at break, TD	600	%	ASTM D882
OPTICAL PROPERTIES			
Gloss			
45°	50	-	ASTM D2457
Haze ⁽¹⁾	16	%	ASTM D1003
FILM PROPERTIES			
Dart Impact F50	112	g	ASTM D1709

(1) Properties have been measured by producing 30 μ film with 2 BUR using 100% 222WT.

PROCESSING CONDITIONS

Typical processing conditions for 222WT are:

Barrel temperature: 190 - 220°C

Blow up ratio: 2.0 - 3.0