

TECHNICAL DATA SHEET

Polypropylene PPB-M30(K8030)



烟台龙义兴高分子材料有限公司
Longyixing Chemicals Co., Ltd

Product	Polypropylene PPB-M30	TECHNICAL DATA SHEET
HS code	39021000	PPB-M30
Type	PP Co-polymer	
Print Date	Oct 18th, 2020	

Description

Polypropylene, a kind of non-toxic, odorless, tasteless opalescent polymer with high crystallization, the melting point among 164-170°C, the density among 0.90-0.91g/cm³, the molecular weight is about 80,000-150,000. PP is one of the lightest plastic of all varieties at present, particularly stable in water, with a water absorption rate in water for 24 hours is only 0.01%.

Application Direction

The grade produced by the HORIZONE gas-phase polypropylene process of Japanese JPP company. It is mainly used for making washing machine internal and external parts, automotive interior parts, automotive modified materials and other products.

Product Packaging

In 25kg bag, 16MT in one 20fcl without pallet or 26-28MT in one 40HQ without pallet or 700kg jumbo bag, 26-28MT in one 40HQ without pallet.

Typical Characteristic

ITEM	UNIT	INDEX	TEST METHOD
Melt mass flow(MFR) Standard value	g/10min	30	GB/T 3682.1-2018
Melt mass flow(MFR) Deviation value	g/10min	±4.0	GB/T 3682.1-2018
Tensile yield stress	Mpa	≥ 22.0	GB/T 1040.2-2006
Flexural modulus(Ef)	Mpa	≥ 1100	GB/T 9341-2008
Charpy notched impact strength (23°C)	KJ/m2	≥6.5	GB/T 1043.1-2008
Heat deflection temperature under load(Tf0.45)	°C	≥ 90	GB/T 1634.2-2019